

Test Report No.: CE/2016/60101

Page: 1 of 7 Date: 2016/06/07

MINMAX TECHNOLOGY CO., LTD NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN

The following sample(s) was/were submitted and identified by/on behalf of the applicant as:

Sample Submitted By : MINMAX TECHNOLOGY CO., LTD

Sample Description : DC-DC CONVERTER

Style/Item No. : MOWI20-XXXXXC SERIES

: 2016/06/01 Sample Receiving Date

Testing Period : 2016/06/01 TO 2016/06/07

As specified by client, to test Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, **Test Requested**

BBP, DEHP, DIBP contents in the submitted sample.

Test Result(s) : Please refer to next page(s).





No.: CE/2016/60101 Date: 2016/06/07 Page: 2 of 7

MINMAX TECHNOLOGY CO., LTD

NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN



Test Result(s)

PART NAME No.1 MIXED ALL PARTS

| Test Item(s) | Unit | Method | MDL | Result |
|----------------------------|-------|--|-----|--------|
| | Offic | | | No.1 |
| Cadmium (Cd) | mg/kg | With reference to IEC 62321-5 (2013) and performed by ICP-AES. | 2 | n.d. |
| Lead (Pb) | mg/kg | With reference to IEC 62321-5 (2013) and performed by ICP-AES. | 2 | 35.3 |
| Mercury (Hg) | mg/kg | With reference to IEC 62321-4 (2013) and performed by ICP-AES. | 2 | n.d. |
| Hexavalent Chromium Cr(VI) | mg/kg | With reference to IEC 62321 (2008) and performed by UV-VIS. | 2 | n.d. |
| Sum of PBBs | mg/kg | With reference to IEC 62321-6 (2015) and performed by GC/MS. | - | n.d. |
| Monobromobiphenyl | mg/kg | | 5 | n.d. |
| Dibromobiphenyl | mg/kg | | 5 | n.d. |
| Tribromobiphenyl | mg/kg | | 5 | n.d. |
| Tetrabromobiphenyl | mg/kg | | 5 | n.d. |
| Pentabromobiphenyl | mg/kg | | 5 | n.d. |
| Hexabromobiphenyl | mg/kg | | 5 | n.d. |
| Heptabromobiphenyl | mg/kg | | 5 | n.d. |
| Octabromobiphenyl | mg/kg | | 5 | n.d. |
| Nonabromobiphenyl | mg/kg | | 5 | n.d. |
| Decabromobiphenyl | mg/kg | | 5 | n.d. |
| Sum of PBDEs | mg/kg | | - | n.d. |
| Monobromodiphenyl ether | mg/kg | | 5 | n.d. |
| Dibromodiphenyl ether | mg/kg | | 5 | n.d. |
| Tribromodiphenyl ether | mg/kg | | 5 | n.d. |
| Tetrabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Pentabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Hexabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Heptabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Octabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Nonabromodiphenyl ether | mg/kg | | 5 | n.d. |
| Decabromodiphenyl ether | mg/kg | | 5 | n.d. |



No.: CE/2016/60101 Date: 2016/06/07 Page: 3 of 7

MINMAX TECHNOLOGY CO., LTD

NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN

| Test Item(s) | Unit | Method | MDL | Result No.1 |
|--|-------|---|-----|----------------|
| BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7) | mg/kg | With reference to IEC 62321-8/CD (2013). Analysis was performed by GC/MS. | 50 | n.d. |
| DBP (Dibutyl phthalate) (CAS No.: 84-74-2) | mg/kg | | 50 | n.d. |
| DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7) | mg/kg | | 50 | n.d. |
| DIBP (Di-isobutyl phthalate) (CAS No.: 84-69-5) | mg/kg | | 50 | n.d. |

Note:

1. mg/kg = ppm; 0.1wt% = 1000ppm

2. n.d. = Not Detected

3. MDL = Method Detection Limit

4. " - " = Not Regulated

5. The sample(s) was/were analyzed on behalf of the applicant as mixing sample in one testing. The above result(s) was/were only given as the informality value.



Page: 4 of 7 No.: CE/2016/60101 Date: 2016/06/07

MINMAX TECHNOLOGY CO., LTD NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN



These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr⁶⁺ test method excluded)

Technician: JR Wang Supervisor: Troy Chang

Cutting / Preparation Sample Measurement Cr6+ Hg Pb · Cd (Note**) Acid digestion by suitable acid Microwave digestion with Add appropriate amount depended on different sample HNO₃/HCI/HF of digestion reagent material (as below table) Heat to appropriate Filtration temperature to extract Residue Solution Cool, filter digestate through filter Alkali Fusion 2) HCl to dissolve **ICP-AES** Add diphenyl-carbazide for color development Sample Material **Digestion Acid** Steel, copper, aluminum, solder Aqua regia, HNO₃, HCl, HF, H₂O₂ Glass HNO₃/HF measure the absorbance Gold, platinum, palladium, ceramic Aqua regia

Note** (For IEC 62321)

Silver

Plastic

Others

(1) For non-metallic material, add alkaline digestion reagent and heat to 90~95 ℃.

Added appropriate reagent to total

H₂SO₄, H₂O₂, HNO₃, HCI

(2) For metallic material, add pure water and heat to boiling.

digestion

 HNO_3

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

at 540 nm by UV-VIS



No.: CE/2016/60101 Date: 2016/06/07 Page: 5 of 7

MINMAX TECHNOLOGY CO., LTD

NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN


Analytical flow chart - PBB/PBDE

Technician: Yaling Tu

Supervisor: Troy Chang

First testing process -Optional screen process

Confirmation process





No.: CE/2016/60101 Date: 2016/06/07


Page: 6 of 7

MINMAX TECHNOLOGY CO., LTD NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN

Analytical flow chart - Phthalate

Technician: Andy Shu Supervisor: Troy Chang

[Test method: IEC 62321-8]





Page: 7 of 7 No.: CE/2016/60101 Date: 2016/06/07

MINMAX TECHNOLOGY CO., LTD NO. 18, SIN-SIN ROAD, AN-PING INDUSTRIAL DISTRICT, TAINAN 702, TAIWAN



* The tested sample / part is marked by an arrow if it's shown on the photo. *

CE/2016/60101



CE/2016/60101



** End of Report **